



February 22, 2022

Utelite Corporation  
6375 Three Mile Canyon Road,  
Coalville, UT 84017

Attention: Mr. Jeff Barrick

**Subject: Qualifications Testing of Utelite Structural Blend Lightweight Aggregate**

**Dear: Mr. Jeff Barrick**

Kleinfelder has performed testing, per your request, to verify the conformance of Utelite Structural Blend Lightweight Aggregate with ASTM C330-17 "Standard Specification for Lightweight Aggregates for Structural Concrete".

Upon review of the results, the Utelite Structural Blend Lightweight Aggregates meet C330-17 test requirements for the Calendar Year 2022.

See the following results.

Sincerely,



**Spencer Davis, PE**  
Principal Geotechnical Engineer

849 West Levoy Drive, Suite 200  
Salt Lake City, UT, 84123  
o| (1) 801.261.3336  
d| (1) 801.713.2870  
m| (1) 435.512.0580  
f| (1) 801.261.3306



## REPORT of AGGREGATE PHYSICAL PROPERTIES

**Project:** Utelite Aggregate Qualification Testing  
**Client:** Lafarge Holcim  
**Material Tested:** Structural Blend  
**Source:** Utelite

**Lab No.:** 22-SLC-00033  
**Project No:** 20211829.001A  
**Sampled by:** Utelite  
**Tested by :** D. Aguirre  
**Reviewed by:** K. Lobato

**Report Date:** 2/22/2022  
**Test Date:** 1/10/2022

### Aggregate Physical Properties

SIEVE ANALYSIS		
ASTM C136	AASHTO T27	
Sieve Size	Accum. % Passing	Specifications
12.5 mm (1/2")	100	100
9.5 mm (3/8")	98	90-100
4.75mm (No. 4)	81	65-90
2.36 mm (No. 8)	61	35-65
2.00 mm (No. 10)	55	---
1.18mm (No.16)	38	---
0.600 mm (No.30)	21	---
0.425mm (No. 40)	15	---
0.300mm (No. 50)	12	10-25
0.150mm (No.100)	7	5-15
0.075mm (No. 200)	5.2	0-10

TEST RESULTS				
Standard	CHEMICAL and PHYSICAL PROPERTIES	Results	Specification	
ASTM C40	Organic Impurities	Color Comparison=	<b>Lighter than Standard</b>	Lighter than Standard
ASTM C641	Staining Index	Stain Index=	<b>20</b>	Less than 60
ASTM C114	Loss on Ignition	Loss, %=	<b>0.29</b>	Less Than 5 Percent
ASTM C142	Clay Lumps and Friable Particles	Fine Aggregate, %=	<b>0.17</b>	Less than 2 Percent
ASTM C29	Bulk Density: Dry Loose Condition	Unit Weight, lbs./cu.ft=	<b>64</b>	65 PCF Maximum
ASTM C29	Bulk Density: Saturated Loose Condition	Unit Weight, lbs./cu.ft=	<b>76</b>	No Requirement
ACI 211.2-98	Absorption of Lightweight Fine Aggregate	*Absorption, %=	<b>22.1</b>	No Requirement
ACI 211.2-98	Relative Density of Fine Aggregate (SSD)	Relative Density, (SSD)=	<b>1.873</b>	No Requirement
ASTM C88	Soundness of Aggregtes (Sodium Sulfate)	Soundness Loss, %=	<b>7.7</b>	Less than 12 Percent
ASTM C88	Soundness of Aggregates (Magnesium)	Soundness Loss, %=	<b>6.9</b>	Less than 18 Percent
ASTM C39	Compressive Strength	Average Strength, psi=	<b>5020</b>	4,000 PSI Minimum
ASTM C496	Splitting Tensile Strength	Average Strength, psi=	<b>490</b>	330 PSI Minimum
ASTM C567	Fresh Concrete Density	Density, lbs./cu.ft=	<b>119</b>	No Requirement
ASTM C567	Oven Dry Density	Density, lbs./cu.ft=	<b>108.1</b>	No Requirement
ASTM C567	Approximate Equilibrium Density	Density, lbs./cu.ft=	<b>111.1</b>	No Requirement
ASTM C157	Drying Shrinkage	Shrinkage, %=	<b>0.04</b>	Less than 0.07
ASTM C151	Popouts	Popouts=	<b>No Popouts</b>	No Popouts
ASTM C1260	Potential Alkali Reactivity of Aggregates	Reactivity, %=	<b>0.07</b>	Less than 0.10

\*Absorption is calculated using a minimum soak time of 72-hours