



February 22, 2022

Utelite Corporation
6375 Three Mile Canyon Road,
Coalville, UT 84017

Attention: Mr. Jeff Barrick

Subject: Qualifications Testing of Utelite Medium Structural Lightweight Aggregate

Dear: Mr. Jeff Barrick

Kleinfelder has performed testing, per your request, to verify the conformance of Utelite Medium Structural Lightweight Aggregate with ASTM C330-17 "Standard Specification for Lightweight Aggregates for Structural Concrete".

Upon review of the results, the Utelite Structural Medium Lightweight Aggregates meet C330-17 test requirements for the Calendar Year 2022.

See the following results.

Sincerely,



Spencer Davis, PE
Principal Geotechnical Engineer

849 West Levoy Drive, Suite 200
Salt Lake City, UT, 84123
o| (1) 801.261.3336
d| (1) 801.713.2870
m| (1) 435.512.0580
f| (1) 801.261.3306



REPORT of AGGREGATE PHYSICAL PROPERTIES

Project: Utelite Aggregate Qualification Testing
Client: Lafarge Holcim
Material Tested: Medium Aggregate
Source: Utelite

Lab No.: 22-SLC-00036
Project No: 20211829.001A
Sampled by: Utelite
Tested by : D. Aguirre
Reviewed by: K. Lobato

Report Date: 2/22/2022
Test Date: 1/10/2022

Aggregate Physical Properties

SIEVE ANALYSIS		
ASTM C136	AASHTO T27	
Sieve Size	Accum. % Passing	Specifications
12.5 mm (1/2")	100	100
9.5 mm (3/8")	97	80-100
4.75mm (No. 4)	19	5-40
2.36 mm (No. 8)	1.0	0-20
2.00 mm (No. 10)	0.5	---
1.18mm (No.16)	0.3	0-10
0.600 mm (No.30)	0.3	---
0.425mm (No. 40)	0.3	---
0.300mm (No. 50)	0.3	---
0.150mm (No.100)	0.3	---
0.075mm (No. 200)	0.2	0-10

TEST RESULTS				
Standard	CHEMICAL and PHYSICAL PROPERTIES	Results	Specification	
ASTM C40	Organic Impurities	Color Comparison=	Lighter than Standard	Lighter than Standard
ASTM C641	Staining Index	Stain Index=	20	Less than 60
ASTM C114	Loss on Ignition	Loss, %=	0.28	Less Than 5 Percent
ASTM C142	Clay Lumps and Friable Particles	Fine Aggregate, %=	0.41	Less than 2 Percent
ASTM C29	Bulk Density: Dry Loose Condition	Unit Weight, lbs./cu.ft=	49	65 PCF Maximum
ASTM C29	Bulk Density: Saturated Loose Condition	Unit Weight, lbs./cu.ft=	58	No Requirement
ACI 211.2-98	Absorption of Lightweight Fine Aggregate	*Absorption, %=	17.7	No Requirement
ACI 211.2-98	Relative Density of Fine Aggregate (SSD)	Relative Density, (SSD)=	1.772	No Requirement
ASTM C88	Soundness of Aggregtes (Sodium Sulfate)	Soundness Loss, %=	8.4	Less than 12 Percent
ASTM C88	Soundness of Aggregates (Magnesium)	Soundness Loss, %=	7.6	Less than 18 Percent
ASTM C39	Compressive Strength	Average Strength, psi=	4450	4,000 PSI Minimum
ASTM C496	Splitting Tensile Strength	Average Strength, psi=	440	330 PSI Minimum
ASTM C567	Fresh Concrete Density	Density, lbs./cu.ft=	119	No Requirement
ASTM C567	Oven Dry Density	Density, lbs./cu.ft=	106.6	No Requirement
ASTM C567	Approximate Equilibrium Density	Density, lbs./cu.ft=	109.6	No Requirement
ASTM C157	Drying Shrinkage	Shrinkage, %=	0.05	Less than 0.07
ASTM C151	Popouts	Popouts=	No Popouts	No Popouts
ASTM C1260	Potential Alkali Reactivity of Aggregates	Reactivity, %=	0.07	Less than 0.10

*Absorption is calculated using a minimum soak time of 72-hours